

# **Dev Priya Papers Pvt. Ltd., Meerut**

**Product : ONYX**

**GSM Range – 250 – 450 g/m<sup>2</sup> GREY BACK**

<b>Parameters</b>	<b>GSM-250 ± 3%</b>	<b>GSM-285 ± 3%</b>	<b>GSM-300 ± 3%</b>	<b>GSM-320 ± 3%</b>	<b>GSM-350 ± 3%</b>	<b>GSM-400 ± 3%</b>	<b>GSM-450 ±3%</b>
Brightness % (± 1%)	78	78	78	78	78	78	78
Caliper Microns (± 5%)	300	342	366	390	427	492	558
Bulk cc/gm (± 5%)	1.20	1.20	1.22	1.22	1.22	1.23	1.24
Stiffness							
MD Taber (± 10%)	80	100	120	140	165	250	300
CD Taber (± 10%)	40	50	60	70	75	120	135
Gloss %	45-50	45-50	45-50	45-50	45-50	45-50	45-50
Cobb Top g/m2	40-45	40-45	40-45	40-45	40-45	40-45	40-45
Cobb Bottom g/m2	45-50	45-50	45-50	45-50	45-50	45-50	45-50
Moisture	6.0-7.0	6.0-7.0	6.0-7.0	6.0-7.0	6.5-8.0	6.5-8.0	7.0-8.0
Wax Pick	7A	7A	7A	7A	7A	7A	7A